



TECHNICAL DATA SHEET

TECHNICAL INFORMATION AND APPLICATION INSTRUCTIONS

H.T. SERIES VINYL SCREEN INKS

CODE REF: 460

SUBSTRATES: Pressure-sensitive vinyl films, vinyl coated products. Since there are many hundreds of different plastic surfaces, it is the printer's responsibility to pre-test the inks prior to engaging in a production run. Ideal for thermo-die cutting.

Note: Pre-test for adhesion prior to use in production

END USES : Formulated for screen printing on a wide variety of vinyl and vinyl coated surfaces, typically used for self-adhesive stickers, signage, vehicle signage, PVC decoration.

PRODUCT INFORMATION

The ink will form a positive bond with substrates and produce a fair gloss finish which may be vacuum-formed. Prints will air-dry within 5 to 10 minutes and will jet-dry in seconds at low temperatures. The inks are non-blocking and prints may be stacked once totally dry (See Special Note 8). Colours are formulated for extended outdoor use on request. Suitable for thermo-die cutting.

APPLICATION INFORMATION

MESH 90T and finer meshes are recommended.

STENCIL All direct photoemulsions, photostencil films and hand cut stencil films that are solvent resistant.

SQUEEGEE 70-80 durometer polyurethane blades as well as triple durometer blades that produce an even ink deposit.

COVERAGE 30 - 45 Square meter per 1kg (100T - 120T mesh).

DRYING H.T. Series will air-dry within 2 to 5 minutes, without drying in the screen. The ink will jet-dry at very low temperatures 32°C to 50°C in seconds. These inks will not dry in the screen under normal working conditions and will re-dissolve after extended printing breaks with a few squeegee passes.

THINNERS The inks can be thinned with approximately 5 - 10% of N564 S572 H.T. Thinners, N665 S303 44000 Thinners or N665 S307 H.T. Retarder or Universal Retarder D564 S064.

CLEAN UP N660 S344 Screen wash.



GL Specialized Inks (Pty) Ltd

Registration No.: 1997/13081/007

PO Box 1026
Westville, 3630
SOUTH AFRICA

Tel: +27 (0)31 7006455
Fax: +27 (0)31 7006187
Website: www.gl-inks.com

Email: jay@gl-inks.com
Email: gordon@gl-inks.com

GENERAL GUIDELINES**INK HANDLING**

All personnel mixing and handling inks must wear gloves and eye protection. Clean up spills immediately. If ink does come in contact with skin, wipe off with a clean, dry, absorbent cloth (do not use solvent or thinner). Wash and rinse affected area with soap and water. Consult the HT Series Material Safety Data Sheet for further instructions and warnings.

STORAGE

Store tightly covered at temperatures between 15°C - 32°C. Ink taken from the press should not be returned to the original container. Store separately to avoid contaminating unused ink.

SPECIAL NOTES

1. H.T. inks are not suitable for rigid vinyl's (bottle printing) as these inks tend to feather badly due to static build up. Plastivac Series is recommended for this application.
2. Whilst H.T. Series, 44000 Series and GV Series are used on the same substrates, the resins used in these formulations are very different. Do not interblend.
3. It is possible to overprint H.T. with GV or 44000 Series or vice versa - however, adequate pre-testing must be done.
4. H.T. Series inks are based on less aggressive solvents than GV Series and 44000 Series. Because of these different solvents, H.T. inks produce a less pungent odour in the workplace.
5. When printing on "Banner" type vinyl's, check for adhesion after 24 hours with the following test:

Fold substrate through 180°, ink to ink and ensure a definite crease by going over the fold five (5) times and apply adhesive tape to the fold line. There should be no ink removal. If ink removal is apparent, repeat the test after wiping the surface with Iso Propyl Alcohol or Methylated Spirits before printing.

If ink adhesion is acceptable after wiping with alcohol, this indicates that Plasticizer and/or other surface active agents have migrated to the surface of the vinyl, however, adhesion on ageing, even if the material is alcohol wiped, is likely to deteriorate.

If wiping the substrate is not practical in production, repeat the test using GV inks or 44000 Series.

The adhesion properties of the three ink series vary. Beware that adhesion on "Banner Vinyl's" can deteriorate with age. Softening can also occur due to plasticizer migration and in worst case situations, blocking could occur. The H.T. Series is formulated to be the most resistant to re-softening/blocking; however, good practice must still be followed with dusting/interleaving used as appropriate.
6. H.T. Series of inks, unlike the GV and 44000 series, has been given more of a gel-like structure which is normal with process inks, in order to give sharper dot printing.
7. H.T. Series inks have been designed to minimize inter-coat re-wetting which, when it occurs, results in unhandleable tack build-up. H.T. is therefore, more eminently suitable for multi-layers of ink printing, avoiding incessant wash-ups during the print run.
8. Some PVC's contain large amounts of monomeric plasticizer that may migrate to the surface and cause ink softening, which could lead to blocking. Such materials may need to be interleaved with paper or dusted with powder.



CAUTION

Please proof this ink, reduced to the consistency you wish to adopt, on a sample of the ACTUAL SUBSTRATE you will be printing BEFORE starting a production run.

Give the proof 24 hours to dry out then check for: Abrasion resistance, adhesion, print appearance and correctness of colour. The adequacy of this ink in these properties cannot be fully established on laboratory equipment on a small scale.

GL stands behind the quality of this product. GL cannot, however, guarantee the finished results because GL exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from GL.

Keep away from heat and open flame. Use with adequate ventilation. Avoid prolonged or repeated contact with skin. Avoid prolonged breathing of vapour or spray mist. Keep container closed when not in use.

Last Date Amended: 12 October 2006